



Joint venture between SGS and IMME Mongolia



SGS IMME MONGOLIA LLC

### INSPECTION REPORT

Company : Darkhan Metallurgical Plant  
Location: Tumurtei Terminal  
Date: 2024.4.6

Sample No:	Product weight	H <sub>2</sub> O	Fe	S	Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	TiO <sub>2</sub>	P	Number of Car:	
	ton	%	%	%	%	%	%	%	pcs	
TLot 29	1	671.35	2.18	58.36	0.31	2.14	6.45	0.38	0.01	10
	2	657.65	2.07	59.37	0.30	1.96	5.31	0.32	<0.01	10
	3	704.30	2.06	57.86	0.30	2.15	6.37	0.33	<0.01	10
	4	710.85	2.04	60.28	0.39	1.53	4.99	0.27	0.02	10
	5	419.20	2.12	57.56	0.41	1.85	6.61	0.36	<0.01	6
<b>Average result*</b>	<b>3,163.35</b>	<b>2.09</b>	<b>58.78</b>	<b>0.34</b>	<b>1.93</b>	<b>5.89</b>	<b>0.33</b>	<b>0.01</b>	<b>46</b>	

NOTE: \*Average result of all analytes is for summary of product weight.  
This result format of the inspection sample only for DMP's internal use only.

Signature



SGS-IMME Mongolia LLC